

Trend Editon

Properties

Decorative paint for interior and exterior use on clean, firm and not chalking surfaces.

Application

For interior and exterior application on smaller surfaces off wood, plastic etc.

The substrate must be clean, dry and solid, suitable for paint treatment, free from grease, oil, wax and soap residues.

Prime untreated substrates indoors with Flügger Interior High Finish 5.

Apply Flügger Trend Edition Gold, Silver, Copper with brush. It is recommended to apply paint 3 times by cross-application.

It is not recommended to coat it with varnish.

Treatment is not appropriate for horizontal surfaces outdoors, neither for the places where water can gather.

Stir paint well before and during use.

Produced by Skovgaard & Frydensberg



Technical Data

Product Type	Metal Paint
Gloss	45;Semi Gloss
Nominal spreading rate (m ² /ltr.)	8
Min. working temp. during application and drying/curing	Min. +10°C
Drying time at 20° C, 60 % RH (Hours)	1
Recoatable at 20° C, 60 % RH (Hours)	4
Fully cured at 20° C, 60 % RH (Days)	28
Dilution	Not to be diluted
Cleaning of Tools etc.	Water

Current TDS Version

April 2015

Replaces TDS Version

January 2013